

08/04/98



Jc605 U.S. PTO

Practitioner's Docket No. 50349

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Box Patent Application
Assistant Commissioner for Patents
Washington, D.C. 20231

Jc526 U.S. PTO

09/129113



08/04/98

NEW APPLICATION TRANSMITTAL

Transmitted herewith for filing is the patent application of

Inventor(s): **James F. Cameron, James Michael Mori, George W. Orsula
Guangyu Xu, and Yoshihiro Yamamoto**

WARNING: 37 C.F.R. § 1.41(a)(1) points out:

"(a) A patent is applied for in the name or names of the actual inventor or inventors.

"(1) The inventorship of a nonprovisional application is that inventorship set forth in the oath or declaration as prescribed by § 1.63, except as provided for in § 1.53(d)(4) and § 1.63(d). If an oath or declaration as prescribed by § 1.63 is not filed during the pendency of a nonprovisional application, the inventorship is that inventorship set forth in the application papers filed pursuant to § 1.53(b), unless a petition under this paragraph accompanied by the fee set forth in § 1.17(f) is filed supplying or changing the name or names of the inventor or inventors."

For (title):

**PHOTORESIST COMPOSITIONS AND METHODS AND ARTICLES
OF MANUFACTURE COMPRISING SAME**

CERTIFICATION UNDER 37 C.F.R. 1.10*

(Express Mail label number is mandatory.)

(Express Mail certification is optional.)

I hereby certify that this New Application Transmittal and the documents referred to as attached therein are being deposited with the United States Postal Service on this date August 4, 1998, in an envelope as "Express Mail Post Office to Addressee," mailing Label Number EL014417675US, addressed to the: Assistant Commissioner for Patents, Washington, D.C. 20231.

Deanna M. Landry

(type or print name of person mailing paper)

Deanna M. Landry
Signature of person mailing paper

WARNING: Certificate of mailing (first class) or facsimile transmission procedures of 37 C.F.R. 1.8 cannot be used to obtain a date of mailing or transmission for this correspondence.

***WARNING:** Each paper or fee filed by "Express Mail" **must** have the number of the "Express Mail" mailing label placed thereon prior to mailing. 37 C.F.R. 1.10(b).

"Since the filing of correspondence under § 1.10 without the Express Mail mailing label thereon is an oversight that can be avoided by the exercise of reasonable care, requests for waiver of this requirement will **not** be granted on petition." Notice of Oct. 24, 1996, 60 Fed. Reg. 56,439, at 56,442.

(Application Transmittal [4-1]—page 1 of 11)

1. Type of Application

This new application is for a(n)

(check one applicable item below)

- ☒ Original (nonprovisional)
☐ Design
☐ Plant

WARNING: Do not use this transmittal for a completion in the U.S. of an International Application under 35 U.S.C. 371(c)(4), unless the International Application is being filed as a divisional, continuation or continuation-in-part application.

WARNING: Do not use this transmittal for the filing of a provisional application.

NOTE: If one of the following 3 items apply, then complete and attach ADDED PAGES FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF A PRIOR U.S. APPLICATION CLAIMED and a NOTIFICATION IN PARENT APPLICATION OF THE FILING OF THIS CONTINUATION APPLICATION.

- ☐ Divisional.
☐ Continuation.
☐ Continuation-in-part (C-I-P).

2. Benefit of Prior U.S. Application(s) (35 U.S.C. 119(e), 120, or 121)

NOTE: A nonprovisional application may claim an invention disclosed in one or more prior filed copending nonprovisional applications or copending international applications designating the United States of America. In order for a nonprovisional application to claim the benefit of a prior filed copending nonprovisional application or copending international application designating the United States of America, each prior application must name as an inventor at least one inventor named in the later filed nonprovisional application and disclose the named inventor's invention claimed in at least one claim of the later filed nonprovisional application in the manner provided by the first paragraph of 35 U.S.C. 112. Each prior application must also be:

(i) An international application entitled to a filing date in accordance with PCT Article 11 and designating the United States of America; or

(ii) Complete as set forth in § 1.51(b); or

(iii) Entitled to a filing date as set forth in § 1.53(b) or § 1.53(d) and include the basic filing fee set forth in § 1.16; or

(iv) Entitled to a filing date as set forth in § 1.53(b) and have paid therein the processing and retention fee set forth in § 1.21(f) within the time period set forth in § 1.53(f).

37 C.F.R. § 1.78(a)(1).

NOTE: If the new application being transmitted is a divisional, continuation or a continuation-in-part of a parent case, or where the parent case is an International Application which designated the U.S., or benefit of a prior provisional application is claimed, then check the following item and complete and attach ADDED PAGES FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF PRIOR U.S. APPLICATION(S) CLAIMED.

WARNING: If an application claims the benefit of the filing date of an earlier filed application under 35 U.S.C. 120, 121 or 365(c), the 20-year term of that application will be based upon the filing date of the earliest U.S. application that the application makes reference to under 35 U.S.C. 120, 121 or 365(c). (35 U.S.C. 154(a)(2) does not take into account, for the determination of the patent term, any application on which priority is claimed under 35 U.S.C. 119, 365(a) or 365(b).) For a c-i-p application, applicant should review whether any claim in the patent that will issue is supported by an earlier application and, if not, the applicant should consider canceling the reference to the earlier filed application. The term of a patent is not based on a claim-by-claim approach. See Notice of April 14, 1995, 60 Fed. Reg. 20,195, at 20,205.

(Application Transmittal [4-1]—page 2 of 11)

09125113 "080498

WARNING: When the last day of pendency of a provisional application falls on a Saturday, Sunday, or Federal holiday within the District of Columbia, any nonprovisional application claiming benefit of the provisional application must be filed prior to the Saturday, Sunday, or Federal holiday within the District of Columbia. See 37 C.F.R. § 1.78(a)(3).

- ☐ The new application being transmitted claims the benefit of prior U.S. application(s). Enclosed are ADDED PAGES FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF PRIOR U.S. APPLICATION(S) CLAIMED.

3. Papers Enclosed

- A. Required for filing date under 37 C.F.R. § 1.53(b) (Regular) or 37 C.F.R. § 1.153 (Design) Application

32 Pages of specification

5 Pages of claims

 Sheets of drawing

WARNING: DO NOT submit original drawings. A high quality copy of the drawings should be supplied when filing a patent application. The drawings that are submitted to the Office must be on strong, white, smooth, and non-shiny paper and meet the standards according to § 1.84. If corrections to the drawings are necessary, they should be made to the original drawing and a high-quality copy of the corrected original drawing then submitted to the Office. Only one copy is required or desired. For comments on proposed then-new 37 CFR 1.84, see Notice of March 9, 1988 (1990 O.G. 57-62).

NOTE: "Identifying indicia, if provided, should include the application number or the title of the invention, inventor's name, docket number (if any), and the name and telephone number of a person to call if the Office is unable to match the drawings to the proper application. This information should be placed on the back of each sheet of drawing a minimum distance of 1.5 cm. (5/8 inch) down from the top of the page . . ." 37 C.F.R. 1.84(c)).

(complete the following, if applicable)

- ☐ The enclosed drawing(s) are photograph(s), and there is also attached a "PETITION TO ACCEPT PHOTOGRAPH(S) AS DRAWING(S)." 37 C.F.R. 1.84(b).
- ☐ formal
- ☐ informal

B. Other Papers Enclosed

 Pages of declaration and power of attorney

1 Pages of abstract

 Other

4. Additional papers enclosed

- ☐ Amendment to claims
- ☐ Cancel in this applications claims _____ before calculating the filing fee. (At least one original independent claim must be retained for filing purposes.)
- ☐ Add the claims shown on the attached amendment. (Claims added have been numbered consecutively following the highest numbered original claims.)
- ☐ Preliminary Amendment
- ☐ Information Disclosure Statement (37 C.F.R. 1.98)
- ☐ Form PTO-1449 (PTO/SB/08A and 08B)
- ☐ Citations

- ☐ Declaration of Biological Deposit
- ☐ Submission of "Sequence Listing," computer readable copy and/or amendment pertaining thereto for biotechnology invention containing nucleotide and/or amino acid sequence.
- ☐ Authorization of Attorney(s) to Accept and Follow Instructions from Representative
- ☐ Special Comments
- ☐ Other

5. Declaration or oath (including power of attorney)

NOTE: A newly executed declaration is not required in a continuation or divisional application provided that the prior nonprovisional application contained a declaration as required, the application being filed is by all or fewer than all the inventors named in the prior application, there is no new matter in the application being filed, and a copy of the executed declaration filed in the prior application (showing the signature or an indication thereon that it was signed) is submitted. The copy must be accompanied by a statement requesting deletion of the names of person(s) who are not inventors of the application being filed. If the declaration in the prior application was filed under § 1.47, then a copy of that declaration must be filed accompanied by a copy of the decision granting § 1.47 status or, if a nonsigning person under § 1.47 has subsequently joined in a prior application, then a copy of the subsequently executed declaration must be filed. See 37 C.F.R. §§ 1.63(d)(1)–(3).

NOTE: A declaration filed to complete an application must be executed, identify the specification to which it is directed, identify each inventor by full name including family name and at least one given name, without abbreviation together with any other given name or initial, and the residence, post office address and country or citizenship of each inventor, and state whether the inventor is a sole or joint inventor. 37 C.F.R. § 1.63(a)(1)–(4).

- ☐ Enclosed
- Executed by

(check all applicable boxes)

- ☐ inventor(s).
- ☐ legal representative of inventor(s).
37 CFR 1.42 or 1.43.
- ☐ joint inventor or person showing a proprietary interest on behalf of inventor who refused to sign or cannot be reached.
- ☐ This is the petition required by 37 CFR 1.47 and the statement required by 37 CFR 1.47 is also attached. See item 13 below for fee.

- ☒ Not Enclosed.

NOTE: Where the filing is a completion in the U.S. of an International Application or where the completion of the U.S. application contains subject matter in addition to the International Application, the application may be treated as a continuation or continuation-in-part, as the case may be, utilizing ADDED PAGE FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF PRIOR U.S. APPLICATION CLAIMED.

- ☐ Application is made by a person authorized under 37 C.F.R. 1.41(c) on behalf of all the above named inventor(s).

(The declaration or oath, along with the surcharge required by 37 CFR 1.16(e) can be filed subsequently).

- ☐ Showing that the filing is authorized.
(not required unless called into question. 37 CFR 1.41(d))

6. Inventorship Statement

WARNING: If the named inventors are each not the inventors of all the claims an explanation, including the ownership of the various claims at the time the last claimed invention was made, should be submitted.

The inventorship for all the claims in this application are:

☒ The same.

or

☐ Not the same. An explanation, including the ownership of the various claims at the time the last claimed invention was made,

☐ is submitted.

☐ will be submitted.

7. Language

NOTE: An application including a signed oath or declaration may be filed in a language other than English. An English translation of the non-English language application and the processing fee of \$130.00 required by 37 CFR 1.17(k) is required to be filed with the application, or within such time as may be set by the Office. 37 CFR 1.52(d).

☒ English

☐ Non-English

☐ The attached translation includes a statement that the translation is accurate. 37 C.F.R. 1.52(d).

8. Assignment

☒ An assignment of the invention to Shipley Company, L.L.C. of
Marlborough, Massachusetts

☐ is attached. A separate ☐ "COVER SHEET FOR ASSIGNMENT (DOCUMENT) ACCOMPANYING NEW PATENT APPLICATION" or ☐ FORM PTO 1595 is also attached.

☒ will follow.

NOTE: "If an assignment is submitted with a new application, send two separate letters—one for the application and one for the assignment." Notice of May 4, 1990 (1114 O.G. 77-78).

WARNING: A newly executed "CERTIFICATE UNDER 37 CFR 3.73(b)" must be filed when a continuation-in-part application is filed by an assignee. Notice of April 30, 1993, 1150 O.G. 62-64.

(Application Transmittal [4-1]—page 5 of 11)

0312943 030498

9. **Certified Copy**

Certified copy(ies) of application(s)

Country	Appln. No.	Filed
Country	Appln. No.	Filed
Country	Appln. No.	Filed

from which priority is claimed

☐ is (are) attached.

☐ will follow.

NOTE: The foreign application forming the basis for the claim for priority must be referred to in the oath or declaration. 37 CFR 1.55(a) and 1.63.

NOTE: This item is for any foreign priority for which the application being filed directly relates. If any parent U.S. application or International Application from which this application claims benefit under 35 U.S.C. 120 is itself entitled to priority from a prior foreign application, then complete item 18 on the ADDED PAGES FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF PRIOR U.S. APPLICATION(S) CLAIMED.

10. **Fee Calculation** (37 C.F.R. 1.16)

A. ☒ Regular application

CLAIMS AS FILED				
Number filed	Number Extra	Rate	Basic Fee 37 C.F.R. 1.16(a) \$790.00	
Total				
Claims (37 CFR 1.16(c)) 33 - 20 =	13	×	\$ 22.00	286.00
Independent				
Claims (37 CFR 1.16(b)) 3 - 3 =		×	\$ 82.00	
Multiple dependent claim(s), if any (37 CFR 1.16(d))		+	\$270.00	

☐ Amendment cancelling extra claims is enclosed.

☐ Amendment deleting multiple-dependencies is enclosed.

☐ Fee for extra claims is not being paid at this time.

NOTE: If the fees for extra claims are not paid on filing they must be paid or the claims cancelled by amendment, prior to the expiration of the time period set for response by the Patent and Trademark Office in any notice of fee deficiency. 37 CFR 1.16(d).

Filing Fee Calculation \$ 1,076.00

B. ☐ Design application
(\$330.00—37 CFR 1.16(f))

Filing Fee Calculation \$ _____

C. ☐ Plant application
(\$540.00—37 CFR 1.16(g))

Filing fee calculation \$ _____

1. **Introduction**
 2. **Background**
 3. **Methodology**
 4. **Results**
 5. **Discussion**
 6. **Conclusion**
 7. **References**
 8. **Appendix**
 9. **Figure 1**
 10. **Figure 2**
 11. **Figure 3**
 12. **Figure 4**
 13. **Figure 5**
 14. **Figure 6**
 15. **Figure 7**
 16. **Figure 8**
 17. **Figure 9**
 18. **Figure 10**
 19. **Figure 11**
 20. **Figure 12**
 21. **Figure 13**
 22. **Figure 14**
 23. **Figure 15**
 24. **Figure 16**
 25. **Figure 17**
 26. **Figure 18**
 27. **Figure 19**
 28. **Figure 20**
 29. **Figure 21**
 30. **Figure 22**
 31. **Figure 23**
 32. **Figure 24**
 33. **Figure 25**
 34. **Figure 26**
 35. **Figure 27**
 36. **Figure 28**
 37. **Figure 29**
 38. **Figure 30**
 39. **Figure 31**
 40. **Figure 32**
 41. **Figure 33**
 42. **Figure 34**
 43. **Figure 35**
 44. **Figure 36**
 45. **Figure 37**
 46. **Figure 38**
 47. **Figure 39**
 48. **Figure 40**
 49. **Figure 41**
 50. **Figure 42**
 51. **Figure 43**
 52. **Figure 44**
 53. **Figure 45**
 54. **Figure 46**
 55. **Figure 47**
 56. **Figure 48**
 57. **Figure 49**
 58. **Figure 50**
 59. **Figure 51**
 60. **Figure 52**
 61. **Figure 53**
 62. **Figure 54**
 63. **Figure 55**
 64. **Figure 56**
 65. **Figure 57**
 66. **Figure 58**
 67. **Figure 59**
 68. **Figure 60**
 69. **Figure 61**
 70. **Figure 62**
 71. **Figure 63**
 72. **Figure 64**
 73. **Figure 65**
 74. **Figure 66**
 75. **Figure 67**
 76. **Figure 68**
 77. **Figure 69**
 78. **Figure 70**
 79. **Figure 71**
 80. **Figure 72**
 81. **Figure 73**
 82. **Figure 74**
 83. **Figure 75**
 84. **Figure 76**
 85. **Figure 77**
 86. **Figure 78**
 87. **Figure 79**
 88. **Figure 80**
 89. **Figure 81**
 90. **Figure 82**
 91. **Figure 83**
 92. **Figure 84**
 93. **Figure 85**
 94. **Figure 86**
 95. **Figure 87**
 96. **Figure 88**
 97. **Figure 89**
 98. **Figure 90**
 99. **Figure 91**
 100. **Figure 92**
 101. **Figure 93**
 102. **Figure 94**
 103. **Figure 95**
 104. **Figure 96**
 105. **Figure 97**
 106. **Figure 98**
 107. **Figure 99**
 108. **Figure 100**
 109. **Figure 101**
 110. **Figure 102**
 111. **Figure 103**
 112. **Figure 104**
 113. **Figure 105**
 114. **Figure 106**
 115. **Figure 107**
 116. **Figure 108**
 117. **Figure 109**
 118. **Figure 110**
 119. **Figure 111**
 120. **Figure 112**
 121. **Figure 113**
 122. **Figure 114**
 123. **Figure 115**
 124. **Figure 116**
 125. **Figure 117**
 126. **Figure 118**
 127. **Figure 119**
 128. **Figure 120**
 129. **Figure 121**
 130. **Figure 122**
 131. **Figure 123**
 132. **Figure 124**
 133. **Figure 125**
 134. **Figure 126**
 135. **Figure 127**
 136. **Figure 128**
 137. **Figure 129**
 138. **Figure 130**
 139. **Figure 131**
 140. **Figure 132**
 141. **Figure 133**
 142. **Figure 134**
 143. **Figure 135**
 144. **Figure 136**
 145. **Figure 137**
 146. **Figure 138**
 147. **Figure 139**
 148. **Figure 140**
 149. **Figure 141**
 150. **Figure 142**
 151. **Figure 143**
 152. **Figure 144**
 153. **Figure 145**
 154. **Figure 146**
 155. **Figure 147**
 156. **Figure 148**
 157. **Figure 149**
 158. **Figure 150**
 159. **Figure 151**
 160. **Figure 152**
 161. **Figure 153**
 162. **Figure 154**
 163. **Figure 155**
 164. **Figure 156**
 165. **Figure 157**
 166. **Figure 158**
 167. **Figure 159**
 168. **Figure 160**
 169. **Figure 161**
 170. **Figure 162**
 171. **Figure 163**
 172. **Figure 164**
 173. **Figure 165**
 174. **Figure 166**
 175. **Figure 167**
 176. **Figure 168**
 177. **Figure 169**
 178. **Figure 170**
 179. **Figure 171**
 180. **Figure 172**
 181. **Figure 173**
 182. **Figure 174**
 183. **Figure 175**
 184. **Figure 176**
 185. **Figure 177**
 186. **Figure 178**
 187. **Figure 179**
 188. **Figure 180**
 189. **Figure 181**
 190. **Figure 182**
 191. **Figure 183**
 192. **Figure 184**
 193. **Figure 185**
 194. **Figure 186**
 195. **Figure 187**
 196. **Figure 188**
 197. **Figure 189**
 198. **Figure 190**
 199. **Figure 191**
 200. **Figure 192**
 201. **Figure 193**
 202. **Figure 194**
 203. **Figure 195**
 204. **Figure 196**
 205. **Figure 197**
 206. **Figure 198**
 207. **Figure 199**
 208. **Figure 200**
 209. **Figure 201**
 210. **Figure 202**
 211. **Figure 203**
 212. **Figure 204**
 213. **Figure 205**
 214. **Figure 206**
 215. **Figure 207**
 216. **Figure 208**
 217. **Figure 209**

- WARNING:** *"Status as a small entity must be specifically established in each application or patent in which the status is available and desired. Status as a small entity in one application or patent does not affect any other application or patent, including applications or patents which are directly or indirectly dependent upon the application or patent in which the status has been established. The refiling of an application under § 1.53 as a continuation, division, or continuation-in-part (including a continued prosecution application under § 1.53(d)), or the filing of a reissue application requires a new determination as to continued entitlement to small entity status for the continuing or reissue application. A nonprovisional application claiming benefit under 35 U.S.C. 119(e), 120, 121, or 365(c) of a prior application, or a reissue application may rely on a statement filed in the prior application or in the patent if the nonprovisional application or the reissue application includes a reference to the statement in the prior application or in the patent or includes a copy of the statement in the prior application or in the patent and status as a small entity is still proper and desired. The payment of the small entity basic statutory filing fee will be treated as such a reference for purposes of this section." 37 C.F.R. § 1.28(a)(2).*

☐ Status as a small entity was claimed in prior application
_____ / _____, filed on _____, from which benefit
is being claimed for this application under:

- and which status as a small entity is still proper and desired.

- Filing Fee Calculation (50% of A, B or C above)**

\$ _____

12. Request for International-Type Search (37 C.F.R. 1.104(d))

☐ Please prepare an international-type search report for this application at the time when national examination on the merits takes place.

(Application Transmittal [4-1]—page 7 of 11)

13. Fee Payment Being Made at This Time

☐ Not Enclosed

☐ No filing fee is to be paid at this time.

(This and the surcharge required by 37 C.F.R. 1.16(e) can be paid subsequently.)

☒ Enclosed

☒ Filing fee

\$ 1,076.00

☐ Recording assignment

(\$40.00; 37 C.F.R. 1.21(h))

(See attached "COVER SHEET FOR ASSIGNMENT ACCOMPANYING NEW APPLICATION".)

\$ _____

☐ Petition fee for filing by other than all the inventors or person on behalf of the inventor where inventor refused to sign or cannot be reached

(\$130.00; 37 C.F.R. 1.47 and 1.17(i))

\$ _____

☐ For processing an application with a specification in

a non-English language

(\$130.00; 37 C.F.R. 1.52(d) and 1.17(k))

\$ _____

☐ Processing and retention fee

(\$130.00; 37 C.F.R. 1.53(d) and 1.21(l))

\$ _____

☐ Fee for international-type search report

(\$40.00; 37 C.F.R. 1.21(e))

\$ _____

NOTE: 37 CFR 1.21(f) establishes a fee for processing and retaining any application that is abandoned for failing to complete the application pursuant to 37 CFR 1.53(f) and this, as well as the changes to 37 CFR 1.53 and 1.78(a)(1), indicate that in order to obtain the benefit of a prior U.S. application, either the basic filing fee must be paid, or the processing and retention fee of § 1.21(f) must be paid, within 1 year from notification under § 53(f).

Total fees enclosed

\$ 1,076.00

14. Method of Payment of Fees

☒ Check in the amount of \$ 1,076.00

☐ Charge Account No. _____ in the amount of \$ _____

A duplicate of this transmittal is attached.

NOTE: Fees should be itemized in such a manner that it is clear for which purpose the fees are paid. 37 CFR 1.22(b).

15. Authorization to Charge Additional Fees

WARNING: If no fees are to be paid on filing, the following items should not be completed.

WARNING: Accurately count claims, especially multiple dependent claims, to avoid unexpected high charges, if extra claim charges are authorized.

- ☒ The Commissioner is hereby authorized to charge the following additional fees by this paper and during the entire pendency of this application to Account No. 07-1526:

☒ 37 C.F.R. 1.16(a), (f) or (g) (filing fees)

☒ 37 C.F.R. 1.16(b), (c) and (d) (presentation of extra claims)

NOTE: Because additional fees for excess or multiple dependent claims not paid on filing or on later presentation must only be paid or these claims cancelled by amendment prior to the expiration of the time period set for response by the PTO in any notice of fee deficiency (37 CFR 1.16(d)), it might be best not to authorize the PTO to charge additional claim fees, except possibly when dealing with amendments after final action.

☒ 37 C.F.R. 1.16(e) (surcharge for filing the basic filing fee and/or declaration on a date later than the filing date of the application)

☐ 37 C.F.R. §§ 1.17(a)(1)–(5) (extension fees pursuant to § 1.136(a)).

☒ 37 C.F.R. 1.17 (application processing fees)

NOTE: ". . . A written request may be submitted in an application that is an authorization to treat any concurrent or future reply, requiring a petition for an extension of time under this paragraph for its timely submission, as incorporating a petition for extension of time for the appropriate length of time. An authorization to charge all required fees, fees under § 1.17, or all required extension of time fees will be treated as a constructive petition for an extension of time in any concurrent or future reply requiring a petition for an extension of time under this paragraph for its timely submission. Submission of the fee set forth in § 1.17(a) will also be treated as a constructive petition for an extension of time in any concurrent reply requiring a petition for an extension of time under this paragraph for its timely submission." 37 C.F.R. § 1.136(a)(3).

☐ 37 C.F.R. 1.18 (issue fee at or before mailing of Notice of Allowance, pursuant to 37 C.F.R. 1.311(b))

NOTE: Where an authorization to charge the issue fee to a deposit account has been filed before the mailing of a Notice of Allowance, the issue fee will be automatically charged to the deposit account at the time of mailing the notice of allowance. 37 CFR 1.311(b).

NOTE: 37 CFR 1.28(b) requires "Notification of any change in status resulting in loss of entitlement to small entity status must be filed in the application . . . prior to paying, or at the time of paying, . . . the issue fee. . . ." From the wording of 37 CFR 1.28(b), (a) notification of change of status must be made even if the fee is paid as "other than a small entity" and (b) no notification is required if the change is to another small entity.

(Application Transmittal [4-1]—page 9 of 11)

0942943 060496
E T S E T S

16. Instructions as to Overpayment

NOTE: "... Amounts of twenty-five dollars or less will not be returned unless specifically requested within a reasonable time, nor will the payer be notified of such amounts; amounts over twenty-five dollars may be returned by check or, if requested, by credit to a deposit account." 37 C.F.R. § 1.26(a).

- ☒ Credit Account No. 07-1526
☐ Refund

864000 "E F T 62 F 60

Reg. No. 33,860

Tel. No. (508) 485-7772

Customer No.



SIGNATURE OF PRACTITIONER

Peter F. Corless

(type or print name of attorney)

P.O. Box 556

P.O. Address

Marlborough, MA 01752

☐ **Incorporation by reference of added pages**

(check the following item if the application in this transmittal claims the benefit of prior U.S. application(s) (including an international application entering the U.S. stage as a continuation, divisional or C-I-P application) and complete and attach the ADDED PAGES FOR NEW APPLICATION TRANSMITTAL WHERE BENEFIT OF PRIOR U.S. APPLICATION(S) CLAIMED)

- ☐ Plus Added Pages for New Application Transmittal Where Benefit of Prior U.S. Application(s) Claimed

Number of pages added _____

- ☐ Plus Added Pages for Papers Referred to in Item 4 Above

Number of pages added _____

- ☐ Plus added pages deleting names of inventor(s) named in prior application(s) who is/are no longer inventor(s) of the subject matter claimed in this application.

Number of pages added _____

- ☐ Plus "Assignment Cover Letter Accompanying New Application"

Number of pages added _____

☒ **Statement Where No Further Pages Added**

(if no further pages form a part of this Transmittal, then end this Transmittal with this page and check the following item)

- ☒ This transmittal ends with this page.

0912913 090498
364090 CTF5T50

PHOTORESIST COMPOSITIONS AND METHODS AND ARTICLES OF
MANUFACTURE COMPRISING SAME

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to new photoresist compositions that can exhibit significantly improved shelf life and lithographic performance.

5

2. Background Art

Photoresists are photosensitive films for transfer of images to a substrate. They form negative or positive images. After coating a photoresist on a substrate, the coating is exposed through a patterned photomask to a source of activating energy such as ultraviolet light to form a latent image in the photoresist coating. The photomask has areas opaque and transparent to activating radiation that define a desired image to be transferred to the underlying substrate. A relief image is provided by development of the latent image pattern in the resist coating. The use of photoresists is generally described, for example, by Deforest, Photoresist Materials and Processes, McGraw Hill Book Company, New York (1975), and by Moreau, Semiconductor Lithography, Principles, Practices and Materials, Plenum Press, New York (1988).

More recently, certain "chemically amplified" photoresist compositions have been reported. Such photoresists may be negative-acting or positive-acting and rely on multiple crosslinking events (in the case of a negative-acting resist) or deprotection reactions (in the case of a positive-acting resist) per unit of photogenerated acid. In other words, the photogenerated acid acts catalytically. In the case of positive chemically amplified resists, certain cationic photoinitiators have been used to induce cleavage of certain "blocking" groups pendant from a photoresist binder, or cleavage of certain groups that comprise a photoresist binder backbone. See, for example, U.S. Patents Nos.

5,075,199; 4,968,851; 4,883,740; 4,810,613; and 4,491,628, and Canadian Patent Application 2,001,384. Upon selective cleavage of the blocking group through exposure of a coating layer of such a resist, a polar functional group is provided, e.g., carboxyl, phenol or imide, which results in different solubility characteristics in exposed and unexposed areas of the resist coating layer.

With the desire to produce high-density semiconductor devices, there is a movement in the industry to shorten the wavelength of exposure sources and use deep U.V. radiation. Such photoresists offer the potential of forming images of smaller features than may be possible at longer wavelength exposure. As is recognized by those in the art, "deep UV radiation" refers to exposure radiation having a wavelength in the range of 350 nm or less, more typically in the range of 300 nm or less such as radiation provided by a KrF excimer laser light (248 nm) or an ArF excimer laser light (193 nm).

An important property of a photoresist is image resolution. A developed photoresist image of fine line definition, including lines of sub-micron and sub-half micron dimensions and having vertical or essentially vertical sidewalls is highly desirable to permit accurate transfer of circuit patterns to an underlying substrate. However, many current photoresists are not capable of providing highly resolved fine line images.

Another important property of a photoresist is photospeed, which can be defined as the exposure time coupled with the exposure energy required to activate the photoactive component, e.g. to generate a sufficient amount of photoacid to provide the desired solubility differential between exposed and unexposed areas of a photoresist coating layer.

It can be critical that a resist's photospeed is within an acceptable and consistent range or value to permit desired processing of the resist. For instance, sufficiently high photospeed is important in many processes, e.g. where a number of exposures are needed such as in generating multiple patterns by a step and repeat process, or where activating

radiation of reduced intensity is employed. Sufficiently high photospeed also permits reduction in the concentration of the radiation sensitive component in the photoresist. On the other hand, a resist that is "too fast", i.e. has too high photospeed, also can be undesirable. For example, an extremely high photospeed may compromise resolution of the patterned resist image, or exposure equipment may not be well suited to image such a fast resist.

Additionally, a consistent resist photospeed can be critical, e.g. so that a device manufacturer can use the same imaging conditions and obtain consistent results despite lot-to-lot differences of a resist product (such as precise amount and/or nature of the photoacid generator, polymer, etc.) that may frequently occur, particularly in large scale resist manufacturing processes. However, many current resists do not exhibit such consistent photospeed, and consequently a device manufacturer may either realize inconsistent results as different lots of a resist formulation are used, or the device manufacturer may be forced to carefully test the photospeed of each new lot of resist and then adjust the parameters of the exposure equipment to provide for consistent processing. Clearly, either alternative is undesirable.

Photospeed variations during storage also are indicative of resist degradation. For example, decreased photospeed of a resist upon storage can indicate degradation of the photoactive compound or other resist components. Storage stability is typically of high importance for a photoresist. Generally, after photoresist manufacture, a resist is stored for several months or more prior to use by a device manufacture. Any resist degradation during storage typically will only compromise lithographic properties.

It thus would be desirable to have new photoresist compositions that could provide highly resolved fine line images. It would be further desirable to have such new photoresist compositions exhibit consistent photospeed. It would be particularly desirable to have such new photoresists that show good storage stability, e.g. as indicated by consistent photospeed over time.

SUMMARY OF THE INVENTION

We have now discovered new positive-acting chemically-amplified photoresist compositions that can provide excellent lithographic performance as well as significantly enhanced storage stability.

5

More particularly, the invention provides photoresist compositions that comprise a solvent that is free of hydroxy groups (i.e. non-hydroxylic solvent), a resin binder and a sulfonium photoacid generator compound (PAG) that exhibits enhanced solubility in the solvent. These resists also can exhibit excellent storage stability, e.g. as exhibited by
10 consistent photospeed over extended storage times.

Non-hydroxylic photoresist solvents, such as propylene glycol methyl ether acetate (PMA) or other glycol alkyl ether acetates, generally exhibit decreased solubility characteristics, particularly with respect to onium salt PAGs, relative to hydroxylic
15 photoresist solvents such as ethyl lactate. However, the resists of the invention exhibit exceptionally good solubility characteristics and storage stability when formulated in PMA and other non-hydroxylic solvents.

Preferred photoacid generator compounds of the invention for use with a non-
20 hydroxylic solvent include sulfonium salts that contain lipophilic moieties. Such moieties have been found to impart enhanced solubility characteristics to the photoactive compound, and ultimately enable significantly increased storage stability of a resist containing the PAG. See the results of the examples which follow. Preferred lipophilic PAGs of the invention have one or more alkyl or heteroalkyl substituents, with each
25 substituent having 2 or more carbon atoms, more preferably 3 or more carbon atoms, still more preferably about 4, 5, 6, 7, 8, 9, 10, 11 or 12 or more carbon atoms. Alkoxy is a preferred heteroalkyl, although other groups can be employed, such as alkylsulfide, alkylsulfinyl, alkylsulfonyl, aminoalkyl, etc.

30

Additional preferred photoacid generator compounds of the invention for use with

0946543.00453

a non-hydroxylic solvent are triarylsulfonium salts that have optionally substituted arylsulfonate counter anions, optionally substituted alicyclic sulfonate counter anions, or optionally substituted acyclic (i.e. noncyclic) sulfonate counter anions.

- 5 Preferred arylsulfonate counter anions in this aspect of the invention include halo- or haloalkyl-substituted arylsulfonate anions, or arylsulfonate anions substituted with other electron-withdrawing groups such as nitro, cyano and the like. For example, preferred counter anions include fluoro(C₁₋₁₆)benzenesulfonate such as 3,5,- bis(trifluoromethyl)benzenesulfonate, 4-trifluoromethylbenzenesulfonate,
- 10 perfluorooctanesulfonate and other perfluoroalkylarylsulfonate and perfluoroalkylsulfonate such as perfluorohexanesulfonic acid, perfluoro(4-ethylcyclohexane)sulfonic acid, perfluorobutanesulfonic acid and the like; halobenzenesulfonate, particularly fluorobenzenesulfonate including pentafluorobenzenesulfonate and the like; nitrobenzenesulfonate such as 2,4-
- 15 dinitrobenzenesulfonate and the like. Preferred alicyclic sulfonate counter anions include optionally substituted single ring groups such as cyclohexyl sulfonate, cycloheptylsulfonate, and more preferably optionally substituted multiple ring groups (e.g. about 2, 3 or 4 bridged or otherwise linked alicyclic groups) such as camphor sulfonate, adamantyl sulfonate and the like. Substituents of substituted alicyclic groups include
- 20 keto (e.g. as in the case of camphor sulfonate where the ring carbon contains a keto substituent), alkyl having 1 to about 16 carbons, alkenyl or alkynyl having 2 to about 16 carbons (e.g. as in the case of camphene) and the like. Phenyl is a generally preferred aryl group of the arylsulfonate anions, although other aryl groups such as naphthyl and the like also can be suitable. Phenyl also is a preferred aryl group of the triarylsulfonium
- 25 compound, i.e. triphenylsulfonium PAGs are preferred, especially when combined with an optionally substituted sulfonate counter anion as described above.

The resin binder component of resists of the invention can be a wide variety of materials. Preferred are chemically amplified positive-acting resists that comprise a resin

30 that contains photoacid labile groups, e.g. resins that contain photoacid-labile acetal or

ketal groups such as disclosed in European Patent Application 0829766A2 of the Shipley Company, or other resins such as the copolymers described in European Patent Application EP0783136A2 of the Shipley Company. While acetals and ketals are generally preferred photoacid labile groups for use with a non-hydroxylic solvent, other acid labile groups also will be suitable, such as acid sensitive esters, carbonates, ethers, imides, etc. The photoacid labile groups will more typically be pendant from a polymer backbone, although resins that have acid labile groups that are integral to the polymer backbone also may be employed.

10 In this aspect of the invention, preferably the solvent component will substantially, essentially or completely be formed from one or more non-hydroxylic solvents, with only a minor portion of a hydroxy-solvent such as ethyl lactate. More particularly, as referred to herein, a solvent component (i.e. all non-solid additives of a resist formulation) will substantially comprise one or more non-hydroxylic solvents where the non-hydroxylic solvent content is present in an amount of at least about 80 wt% or 85 wt %, based on total weight of the solvent component. A solvent component will essentially comprise one or more non-hydroxylic solvents where the non-hydroxylic solvent content is present in an amount of at least about 90 wt%, 92 wt %, 95 wt% or 97 wt%, based on total weight of the solvent component. A solvent component will consist of only one or more non-hydroxylic solvents where the non-hydroxylic solvent(s) are present in least about 98 wt% or 99 wt %, based on total weight of the solvent component.

25 In a further aspect, the invention provides methods for enhancing storage stability of positive chemically-amplified photoresist compositions that comprise a hydroxy-containing solvent (e.g. ethyl lactate), a photoacid-deblocking component which is typically a resin binder and one or more arylsulfonium compounds, particularly one or more arylsulfonium PAGs, e.g. one or more of the same or different triarylsulfonium PAGs, such as those discussed above, that are preferably complexed with a sulfonate counter anion, such as the aryl, alicyclic or acyclic sulfonate counter anions as described

30

09169413-080498

herein.

We have surprisingly found that use of such arylsulfonium compounds can provide significantly enhanced storage stability relative to an otherwise comparable resist that contains a distinct PAG such as an diaryliodonium PAG. See, for instance, the results of Examples 3 and 3a which follow.






The invention further provides methods for forming photoresist relief images and novel articles of manufacture comprising substrates such as a microelectronic wafer or a flat panel display substrate that have been coated with a photoresist composition of the invention. Other aspects of the invention are disclosed *infra*.

DETAILED DESCRIPTION OF THE INVENTION

As discussed above, preferred photoresists of the invention comprise a non-hydroxylic solvent such as PMA, a resin binder and a photoacid generator compound (PAG) that exhibits enhanced solubility in the solvent.

In one aspect, the PAG contains one or more lipophilic moieties, particularly one or more optionally substituted alkyl or heteroalkyl moieties having 2 or more carbons, preferably one or more optionally substituted C₂₋₂₀ alkyl or C₂₋₂₀ heteroalkyl moieties, more typically one or more optionally substituted C₂₋₁₆ alkyl or C₂₋₁₆ heteroalkyl moieties. A generally preferred heteroalkyl is alkoxy having one or more oxygen linkages, typically 1-3 oxygen linkages.

Preferably the PAG that is substituted with one or more lipophilic moieties is a sulfonium compound, particularly an arylsulfonium compound such as a phenylsulfonium compound. For example, suitable PAGs include compounds of any of the following Formulae I through V:



wherein in each of the above formulae (I) through (V), each R is independently an optionally substituted aryl group, with at least one or the R groups of a compound of any
15 of the above formulae being aryl substituted with one or more optionally substituted alkyl or heteroalkyl having 2 or more carbon atoms, preferably 3 or more carbon atoms;


in Formulae IV and V, R² and R^{2'} are members of a first fused aryl ring; each R³ and R^{3'} are members of a second fused aryl ring, and where such first and second fused aryl rings may optionally substituted with one or more R groups as defined above;

20 each X is independently a hetero atom (N, O or S, preferably O or S), a C₁₋₃ alkylene, or a hetero-substituted C₁₋₃ alkylene;

and each M in the above formulae is the same or different and is a counter anion.

In those Formulae I through V, R is preferably a phenyl group, although other aryl
25 groups also will be suitable such as naphthyl, acenaphthyl, etc. Preferred PAGs of the Formulae I through V above include those that have two or more R groups that contain longer chain alkyl or heteroalkyl substituents. Preferred R groups include those having about 3 or 4 or more carbon atoms, even more preferably about 5 or 6 or more carbon atoms, still more preferably about 7 or 8 or more carbon atoms. Alkyl and alkoxy are
30 generally preferred R groups.

Additional preferred PAGs for use in resists that have non-hydroxylic solvents are triarylsulfonium compounds that have long chain substitution on at least one aryl group, and are substituted with distinct groups on one or both of the other aryl groups of the compound; i.e., the compounds are asymmetrically substituted. For instance, suitable asymmetric triphenyl sulfonium PAGs for use in accordance with the invention include compounds of the following of the following Formula VI:



wherein each R is independently alkyl or heteroalkyl having 2 or more carbon atoms, preferably having 3 or 4 or more carbon atoms,


wherein each X and Y is independently hydrogen or a non-hydrogen substituent such as halo; nitro; cyano; sulfonyl; optionally substituted alkyl preferably having from 1 to about 20 carbon atoms; optionally substituted alkoxy preferably having from 1 to about 20 carbon atoms; optionally substituted aminoalkyl preferably having from 1 to about 20 carbon atoms; optionally substituted alkylthio preferably having from 1 to about 20 carbon atoms; optionally substituted alkylsulfinyl preferably having from 1 to about 20 carbon atoms; optionally substituted alkylsulfonyl preferably having from 1 to about 20 carbon atoms; optionally substituted aryloxy such as phenoxy; optionally substituted aralkyl such as benzyl; optionally substituted alkanoyl preferably having from 1 to about 20 carbons atoms with acetyl being a preferred group; optionally substituted carbocyclic aryl such as phenyl, naphthyl, biphenyl, and the like; optionally substituted heteroaromatic or heteroalicyclic having 1 to 3 rings, 3 to 8 ring members in each ring and from 1 to 3 hetero atoms; and the like;

with at least one of X and Y being other than hydrogen (a non-hydrogen substituent) and different from R;

M is a counter anion; and

n, o or p are each independently an integer of from 1 to 5, preferably 1 to 4, more preferably 1, 2 or 3.

Preferred compounds of the above Formulae VI include compounds that have one or more two non-hydrogen substituents on each phenyl ring, particularly compounds of the following Formula VIa:



wherein R and M are the same as defined above for Formula VI; X and Y are the same or different non-hydrogen substituents as defined above for Formula VI, and X and Y are each different than R. Para substitution of the phenyl rings by the R, X and Y substituents is generally preferred, although ortho or meta substitution also will be suitable.

Specifically preferred PAGs of Formula VIa include bis-(C₁₋₂₀alkylphenyl)-(C₁₋₂₀alkoxyphenyl)sulfonium salts such as bis-(methylphenyl)-(C₁₋₁₂alkoxyphenyl)sulfonium salt, particularly bis-(methylphenyl)-(C₁₋₁₂alkoxyphenyl)sulfonium salt. Also preferred are PAGs of Formula VIa that has phenyl groups that are each substituted by phenyl, preferably with the R group being branched. For example, such preferred tri-(alkylphenyl)sulfonium salts include bis-(n-C₁₋₁₂alkylphenyl)-(branched-C₁₋₁₂alkylphenyl)sulfonium salt, such as bis-(methylphenyl)-(t-butylphenyl)sulfonium salt, preferably bis-(4-methylphenyl)-(4-t-butylphenyl)sulfonium salt.

5

15

20

25

30

As discussed above, additional preferred photoactive compounds of the invention

for use with a non-hydroxylic solvent are triarylsulfonium salts that have arylsulfonate counter anions, particularly halo- or haloalkyl-substituted arylsulfonate anions, or arylsulfonate anions substituted with other electron-withdrawing groups such as nitro, cyano and the like.

5

As further discussed above, additional preferred photoactive compounds of the invention for use with a non-hydroxylic solvent are triarylsulfonium salts that have alicyclic sulfonate counter anions, particularly multiple-ring groups such as adamantyl and the like.

10

More specifically, preferred counter anions include fluoroalkylarylsulfonates such as fluoro(C₁₋₁₆)benzenesulfonate, particularly perfluoroalkylarylsulfonates such as 3,5,-bis(trifluoromethyl)benzenesulfonate, 4-trifluoromethylbenzenesulfonate, as well as perfluoroalkylsulfonates such as perfluorooctanesulfonate, perfluorohexanesulfonic acid, perfluoro(4-ethylcyclohexane)sulfonic acid, perfluorobutanesulfonic acid and the like; halobenzenesulfonate, particularly fluorobenzenesulfonate including pentafluorobenzenesulfonate and the like; nitrobenzenesulfonate such as 2,4-dinitrobenzenesulfonate and the like. Phenyl is a generally preferred aryl group of the arylsulfonate anions, although other aryl groups such as naphthyl and the like also can be suitable. Preferred alicyclic sulfonate counter anions include single ring groups such as cyclohexyl sulfonate, cycloheptylsulfonate, and more preferably multiple ring groups (e.g. about 2, 3 or 4 bridged or otherwise linked groups) such as camphor sulfonate, adamantyl sulfonate and the like. Preferred substituents of substituted alicyclic groups include keto, halogen particularly fluoro, C₁₋₁₆alkyl, C₂₋₁₆ alkenyl or alkynyl or any of the substituents mentioned above for the arylsulfonate anions. Preferred acyclic sulfonate counter anions include alkyl sulfonate compounds, such as C₁₋₁₆ alkyl sulfonate, more preferably C₃₋₁₂ alkyl sulfonate, that may be optionally substituted with groups such as those mentioned above for alicyclic groups. Preferred substituents for acyclic sulfonate counter anions are one or more halogen, particularly fluoro, especially a perfluoroalkyl sulfonate.

30

PAGs of the above formulae may be preferred by known procedures and as described herein, including in Examples 4 and 5 below. See also U.S. Patent 5,731,364; S.R. Akhtar et al., *Chem. Mater.*, (1990) 2:732; S.R. Akhtar et al., *J. Org. Chem.*, (1990) 55:4222; and Miller et al., *J. Org. Chem.*, (1988) 53:5571, for synthetic methods..

5

The invention further provides methods for enhancing storage stability of photoresist compositions that comprise hydroxy-containing solvent (e.g. ethyl lactate), a resin binder and one or more arylsulfonium compounds. Arylsulfonium compounds discussed above are suitable for this aspect of the invention, particularly PAGs of any one of Formula I through VI and VIa above.

10

As discussed above, photoresists of the invention also contain a deblocking component, which suitably will be a resin binder of a resist. The deblocking component may contain any of a variety of acid labile groups, such as acid sensitive esters, acetals, ketals and the like, which suitably may be pendant from a polymer backbone. Acid labile groups that are integral to the polymer backbone also may be employed. Preferred deblocking resin binders have also been disclosed in European Patent Published Application EP0813113A1 and European Patent Application 97115532 (corresponding to U.S. application serial number 08/706,138), and in U.S. Patent 5,258,257 to Sinta et al. Suitable deblocking resins and use of same in chemically amplified photoresists also have been described in U.S. Patents Nos. 4,968,581; 4,883,740; 4,810,613; 4,491,628 and 5,492,793.


15

20

Preferred deblocking resins for use in the resists of the invention include polymers that contain both phenolic and non-phenolic units. For example, one preferred group of such polymers has acid labile groups substantially, essentially or completely only on non-phenolic units of the polymer. One preferred polymer binder has repeating units x and y of the following formula:

25

30




5 wherein the hydroxyl group be present at either the ortho, meta or para positions throughout the polymer, and R' is substituted or unsubstituted alkyl having 1 to about 18 carbon atoms, more typically 1 to about 6 to 8 carbon atoms. *Tert*-butyl is a generally preferred R' group. An R' group may be optionally substituted by e.g. one or more halogen (particularly F, Cl or Br), C₁₋₈ alkoxy, C₂₋₈ alkenyl, etc. The depicted phenolic

10 units of the polymer also may be optionally substituted by such groups. The units x and y may be regularly alternating in the polymer, or may be randomly interspersed through the polymer. Such copolymers can be readily formed. For example, for resins of the above formula, vinyl phenols and a substituted or unsubstituted alkyl acrylate such as *t*-butylacrylate and the like may be condensed under free radical conditions as known in the

15 art. The substituted ester moiety, i.e. R'-O-C(=O)-, of the acrylate units serves as the acid labile groups of the resin and will undergo photoacid induced cleavage upon exposure of a coating layer of a photoresist containing the resin. Preferably the copolymer will have a Mw of from about 3,000 to about 50,000, more preferably about 10,000 to about 30,000 with a molecular weight distribution of about 3 or less, more preferably a molecular


20 weight distribution of about 2 or less. Such copolymers also may be prepared by such free radical polymerization or other known procedures and suitably will have a Mw of from about 3,000 to about 50,000, and a molecular weight distribution of about 3 or less, more preferably a molecular weight distribution of about 2 or less.

25 Additional preferred deblocking resins have acid labile groups on both phenolic and non-phenolic units of the polymer. One preferred polymer binder has repeating units a, b and c of the following formula:



wherein R' group is a photoacid labile group as defined above for the other preferred polymer; X is another repeat unit which may or may not contain a photoacid labile group; and each Y is independently hydrogen or C₁₋₆ alkyl, preferably hydrogen or methyl. The values a, b and c designate the molar amount of the polymer units. Those polymer units may be regularly alternating in the polymer, or may be randomly interspersed through the polymer. Suitable X groups may be aliphatic or aromatic groups such as phenyl, cyclohexyl, adamantyl, isobornyl, optionally containing an acid labile group. Such polymers may be formed in the same manner as described for the polymer above, and wherein the formed copolymer is reacted to provide the phenolic acid labile groups.

Additional preferred deblocking resins include at least three distinct repeating units of 1) units that contain acid-labile groups; 2) units that are free of reactive groups as well as hydroxy groups; and 3) aromatic or other units that contribute to aqueous developability of a photoresist containing the polymer as a resin binder. Particularly preferred deblocking polymers of this type correspond to the following Formula I:



wherein R of units 1) is substituted or unsubstituted alkyl preferably having 1 to about 10 carbon atoms, more typically 1 to about 6 carbons. Branched alkyl such as *tert*-butyl are generally preferred R groups. Also, the polymer may comprise a mixture of different R groups, e.g., by using a variety of acrylate monomers during the polymer synthesis.

R^I groups of units 2) of the above Formula I each independently may be e.g. halogen (particularly F, Cl and Br), substituted or unsubstituted alkyl preferably having 1

to about 8 carbons, substituted or unsubstituted alkoxy preferably having 1 to about 8 carbon atoms, substituted or unsubstituted alkenyl preferably having 2 to about 8 carbon atoms, substituted or unsubstituted alkynyl preferably having 2 to about 8 carbons, substituted or unsubstituted alkylthio preferably having 1 to about 8 carbons, cyano, nitro, etc.; and m is an integer of from 0 (where the phenyl ring is fully hydrogen-substituted) to 5, and preferably is 0, 1 or 2. Also, two R¹ groups on adjacent carbons may be taken together to form (with ring carbons to which they are attached) one, two or more fused aromatic or alicyclic rings having from 4 to about 8 ring members per ring. For example, two R¹ groups can be taken together to form (together with the depicted phenyl) a naphthyl or acenaphthyl ring. As with units 1), the polymer may comprise a mixture of different units 2) with differing R¹ groups or no R¹ groups (i.e. m=0) by using a variety of substituted or unsubstituted vinylphenyl monomers during the polymer synthesis.

R² groups of units 3) of the above Formula I each independently may be e.g. halogen (particularly F, Cl and Br), substituted or unsubstituted alkyl preferably having 1 to about 8 carbons, substituted or unsubstituted alkoxy preferably having 1 to about 8 carbon atoms, substituted or unsubstituted alkenyl preferably having 2 to about 8 carbon atoms, substituted or unsubstituted sulfonyl preferably having 1 to about to about 8 carbon atoms such as mesyl (CH₃SO₂O-), substituted or unsubstituted alkyl esters such as those represented by RCOO- where R is preferably an alkyl group preferably having 1 to about 10 carbon atoms, substituted or unsubstituted alkynyl preferably having 2 to about 8 carbons, substituted or unsubstituted alkylthio preferably having 1 to about 8 carbons, cyano, nitro, etc.; and p is an integer of from 0 (where the phenyl ring has a single hydroxy substituent) to 4, and preferably is 0, 1 or 2. Also, two R² groups on adjacent carbons may be taken together to form (with ring carbons to which they are attached) one, two or more fused aromatic or alicyclic rings having from 4 to about 8 ring members per ring. For example, two R² groups can be taken together to form (together with the phenol depicted in Formula I) a naphthyl or acenaphthyl ring. As with units 1), the polymer may comprise a mixture of different units 3) with differing R² groups or no R² groups (i.e. p=0) by using a variety of substituted or unsubstituted vinylphenyl monomers during the

polymer synthesis. As shown in Formula I above, the hydroxyl group of units 3) may be either at the ortho, meta or para positions throughout the copolymer. Para or meta substitution is generally preferred.

- 5 Each R^3 , R^4 and R^5 substituent independently may be hydrogen or substituted or unsubstituted alkyl preferably having 1 to about 8 carbon atoms, more typically 1 to about 6 carbons, or more preferably 1 to about 3 carbons.




- 10 The above-mentioned substituted groups (i.e. substituted groups R and R^1 through R^5 of Formula I above) may be substituted at one or more available positions by one or more suitable groups such as halogen (particularly F, Cl or Br); C_{1-8} alkyl; C_{1-8} alkoxy; C_{2-8} alkenyl; C_{2-8} alkynyl; aryl such as phenyl; alkanoyl such as a C_{1-6} alkanoyl of acyl and the like; etc. Typically a substituted moiety is substituted at one, two or three available positions.


- 15 In the above Formula I, x, y and z are the mole fractions or percents of units 3), 2) and 1) respectively in the copolymer. These mole fractions may suitably vary over rather wide values, e.g., x may be suitably from about 10 to 90 percent, more preferably about 20 to 90 percent; y may be suitably from about 1 to 75 percent, more preferably about 2
20 to 60 percent; and z may be 1 to 75 percent, more preferably about 2 to 60 percent.

- 25 Preferred copolymers of the above Formula I include those where the only polymer units correspond to the general structures of units 1), 2) and 3) above and the sum of the mole percents x, y and z equals one hundred. However, preferred polymers also may comprise additional units wherein the sum of x, y and z would be less than one hundred, although preferably those units 1), 2) and 3) would still constitute a major portion of the copolymer, e.g. where the sum of x, y and z would be at least about 50 percent (i.e. at least 50 molar percent of the polymer consists of units 1), 2) and 3)), more preferably the sum of x, y and z is at least 70 percent, and still more preferably the sum of
30 x, y and z is at least 80 or 90 percent. See European Published Patent Application EP

0813113A1 for detailed disclosure of free radical synthesis of copolymers of the above Formula I.

For resists of the invention formulated in non-hydroxylic solvents such as PMA,
 5 particularly suitable resin binders include those that have acetalester and/or ketalester
 deblocking groups. Such resins are disclosed in EP 0829766A2 of the Shipley Company
 and U. Kumar. For instance, suitable resins include terpolymers formed from
 hydroxystyrene, styrene and acid labile components such as 1-propyloxy-1-
 ethylmethacrylate and the like. See the examples of EP 0829766A2, and the examples
 10 herein which follow for particularly suitable polymers. Additionally, preferred acetal or
 ketal polymers include units of any of the following Formula (A), (B), (C) or (D):





wherein the above Formula (A), W is a linker any may be e.g. a chemical bond; an optionally alkylene group preferably having 1 to about 12 carbons; optionally substituted alkenylene preferably having 3 to about 12 carbons; optionally substituted alkynylene preferably having from 3 to about 12 carbons and the like;

in each of the above Formulae (A), (B), (C) and (D), each Z is an independent bridge group between polymer units e.g. optionally substituted alkylene linkage having 1-6 carbons, more typically 1-3 carbons and optionally substituted by C₁₋₂ alkyl;

in each of the above Formulae (A), (B), (C) and (D), U and V each independently may be hydrogen; halogen; optionally substituted alkyl, preferably having from 1 to about 20 carbons, more preferably 1 to about 8 carbons; optionally substituted alkenyl or alkynyl, preferably having from 2 to about 20 carbons, more preferably 2 to about 8 carbons; optionally substituted alkanoyl, preferably having 1 to about 12 carbons, more preferably 1 to about 8 carbons; optionally substituted carbocyclic aryl such as phenyl, preferably having from 6 to about 24 carbons; optionally substituted aralkyl such as benzyl, preferably having from 7 to 24 carbons; optionally substituted heterocyclic or heteroaromatic having 1 to 3 ring members and from 1 to about 3 atoms; and the like, preferably with at least one of U or V being other than hydrogen;

R is optionally substituted alkyl, preferably having 1 to about 20 carbons, more preferably 1 to about 15 carbons; optionally substituted alkenyl or alkynyl, preferably having 2 to about 20 carbons, more preferably 2 to about 15 carbons; optionally

substituted alkanoyl, preferably having 1 to about 20 carbons, more preferably 1 to about 8 carbons; optionally substituted carbocyclic aryl such as phenyl, preferably having 6 to about 24 carbons; optionally substituted aralkyl such as benzyl, preferably having from 7 to 24 carbons; optionally substituted heterocyclic or heteroaromatic having 1 to 3 ring members and from 1 to about 3 atoms; and the like;

or R and at least one of U and V may be taken together with the depicted interposed oxygen to form a ring structure, preferably an alicyclic structure having one, two or more rings, each ring having 4 to about 10 ring members and the U or V and R groups are optionally substituted alkylene or heteroalkylene (i.e. alkylene with a N, O or S linkage). For example, R and at least one of U and V may be taken together with the depicted interposed oxygen (i.e. the oxygen between the groups CUV and R) so as to form e.g. tetrahydropyranyl or tetrahydrofuranyl i.e. acetal/ketalester groups pendant to the polymer backbone of the formulae $-C(=O)-O-(2\text{-tetrahydropyranyl})$ or $-C(=O)-O-(2\text{-tetrahydrofuranyl})$;

in Formula (B), (C) (D), each R^1 is independently halogen, optionally substituted alkyl preferably having 1 to about 12 carbon atoms, optionally substituted alkoxy preferably having 1 to about 12 carbon atoms, optionally substituted alkenyl preferably having 2 to about 12 carbon atoms, optionally substituted alkynyl preferably having 2 to about 12 carbon atoms, optionally substituted alkylthio preferably having 1 to about 12 carbon atoms, cyano, nitro, amino, hydroxy, etc., or two R^1 groups on adjacent carbons may be taken together to form (with ring carbons to which they are attached) one, two or more fused aromatic or alicyclic rings having from 4 to about 8 ring members per ring (such as to form with the depicted phenyl a optionally substituted naphthyl or acenaphthyl ring), and n is an integer of from 0 (where the phenyl ring is fully hydrogen-substituted) to 4, and preferably is 0, 1 or 2;

in Formula (C), T is preferably a high carbon moiety and may be e.g. optionally substituted alkyl having from 4 to about 20 carbons, and preferably is a cyclic group such as adamantyl, norbornyl, isobornyl and the like, or optionally substituted aryl, particularly carbocyclic aryl such as phenyl, naphthyl, acenaphthyl, anthracenyl, phenanthracenyl, etc.; optionally substituted aralkyl such as benzyl, benzhydryl, etc.; or optionally

substituted heterocyclic or heteroaromatic having 1 to 3 ring members and from 1 to about 3 atoms;

x and y are the mole percents of the respective units in the polymer of Formula (B) and (D), and preferably x and y will each be in the range of from about 5 to 90 percent, and more typically x will be from about 50 to 95 mole percent;

x', y' and z' are the mole percents of the respective units in the polymer of Formula (C), and preferably x' is from about 60 to 80 percent, and y' and z' are each from about 10 to 30 mole percent.

10 A preferred optional additive of resists of the invention is an added base, particularly tetrabutylammonium hydroxide (TBAH), which can enhance resolution of a developed resist relief image. A TBAH acetate salt is often preferred, particularly in a PMA-based resist. The added base is suitably used in relatively small amounts, e.g. about 1 to 10 percent by weight relative to the PAC, more typically 1 to about 5 weight
15 percent. Other preferred basic additives include ammonium sulfonate salts such as piperidinium p-toluenesulfonate and dicyclohexylammonium p-toluenesulfonate; alkyl amines such as tripropylamine and dodecylamine; aryl amines such as diphenylamine, triphenylamine, aminephenol, 2-(4-aminophenyl)-2-(4-hydroxyphenyl)propane, etc.

20 Photoresists of the invention also may contain other optional materials. For example, other optional additives include anti-striation agents, plasticizers, speed enhancers, etc. Such optional additives typically will be present in minor concentration in a photoresist composition except for fillers and dyes which may be present in relatively large concentrations such as, e.g., in amounts of from about 5 to 30 percent by weight of
25 the total weight of a resist's dry components.

The compositions of the invention can be readily prepared by those skilled in the art. For example, a photoresist composition of the invention can be prepared by dissolving the components of the photoresist in a suitable solvent as discussed above.

30 Thus, in the first aspect of the invention, the resist is formulated in a non-hydroxylic

solvents such as PMA; EEP (ethyl ethoxy propionate); or other glycol ethers such as 2-methoxyethyl ether (diglyme); ketones such as methyl ethyl ketone, 2-heptanone and cyclohexanone; with PMA being generally preferred.

5 As discussed above, the invention also provides methods for enhancing storage stability of positive-acting chemically amplified photoresist compositions that contain a hydroxy-containing solvent, particularly ethyl lactate or methyl lactate. Other suitable hydroxy-containing solvents include ethylene glycol monomethyl ether and propylene glycol monomethyl ether.

10

Typically, the solids content of a resist of the invention varies between about 5 and 35 percent by weight of the total weight of the photoresist composition. The resin binder and PAG components should be present in amounts sufficient to provide a film coating layer and formation of good quality latent and relief images. See the examples
15 which follow for exemplary preferred amounts of resist components.

15

The resists of the invention are used in accordance with generally known procedures. The liquid coating compositions of the invention are applied to substrate such as by spinning, dipping, roller coating or other technique. When spin coating, the
20 solids content of the coating solution can be adjusted to provide a desired film thickness based upon the specific spinning equipment utilized, the viscosity of the solution, the speed of the spinner and the amount of time allowed for spinning.

20

The resist compositions of the invention are suitably applied to substrates
25 conventionally used in processes involving coating of photoresists. For example, the composition may be applied over silicon or silicon dioxide wafers for the production of microprocessors and other integrated circuit components. Aluminum-aluminum oxide, gallium arsenide, ceramic, quartz or copper substrates also may be employed. Substrates used for liquid crystal display and other flat panel display applications are also suitably
30 employed, e.g. glass substrates, indium tin oxide coated substrates and the like.

30

Following coating of the photoresist onto a surface, it is dried by heating to remove the solvent until preferably the photoresist coating is tack free. Thereafter, it is imaged through a mask in conventional manner. The exposure is sufficient to effectively
5 activate the photoactive component of the photoresist system to produce a patterned image in the resist coating layer and, more specifically, the exposure energy typically ranges from about 1 to 300 mJ/cm², dependent on the exposure tool and the components of the photoresist composition.

10 Coating layers of the resist compositions of the invention are suitably photoactivated by an exposure wavelength in the deep U.V. range i.e., 350 nm or less, more typically in the range of about 300 nm or less, typically about 150 to 300 or 350 nm. A particularly preferred exposure wavelength is about 248 nm.

15 Following exposure, the resist film layer is preferably baked at temperatures ranging from about 50°C to about 160°C to create or enhance solubility differences between exposed and unexposed regions of the resist layer.

After any such post-exposure bake, the patterned film layer is developed,
20 preferably using an aqueous-based developer such as an inorganic alkali exemplified by sodium hydroxide, potassium hydroxide, sodium carbonate, sodium bicarbonate, sodium silicate, sodium metasilicate; quaternary ammonium hydroxide solutions such as a tetra-alkyl ammonium hydroxide solution; various amine solutions such as ethyl amine, n-propyl amine, diethyl amine, di-n-propyl amine, triethyl amine, or methyldiethyl amine;
25 alcohol amines such as diethanol amine or triethanol amine; cyclic amines such as pyrrole, pyridine, etc. In general, development is in accordance with art recognized procedures.

Following development of the photoresist coating over the substrate, the
30 developed substrate may be selectively processed on those areas bared of resist, for

example by chemically etching or plating substrate areas bared of resist in accordance with procedures known in the art. For example, for the manufacture of microelectronic substrates, suitable etchants include a plasma gas etch (e.g. an oxygen plasma etch) and a hydrofluoric acid etching solution. After such processing, resist may be removed from the
5 processed substrate using known stripping procedures.

All documents mentioned herein are incorporated herein in their entirety by reference. The following non-limiting examples are illustrative of the invention.

10 General comments

In the following examples, the term "total solids" refers to all components of the resist formulation other than solvent. Resist samples were filtered to 0.2 μm immediately after preparation. Photospeed (E_0) was calculated as the exposure dose (mj/cm^2) necessary to remove the imaged resist layer upon development. In each of the resist
15 formulations of Examples 1 and 1a below, the resin binder was the same blend of 1) poly(4-hydroxystyrene-co-4-t-butyloxycarbonyloxystyrene) and 2) partially hydrogenated poly(4-hydroxystyrene) modified with ethoxy ethyl protecting on a portion of the phenolic and/or cyclohexanol -OH groups. In each of the resist formulations of Examples 2 and 2a below, the resin binder was the same blend of 1) poly(4-
20 hydroxystyrene-co-4-t-butylacrylate) and 2) partially hydrogenated poly(4-hydroxystyrene) modified with ethoxy ethyl protecting on a portion of the phenolic and/or cyclohexanol -OH groups. In each of the resist formulations of Examples 3 and 3a below, the resin binder was the same blend of 1) poly(4-hydroxystyrene-co-4-t-butylacrylate) and 2) partially hydrogenated poly(4-hydroxystyrene) modified with
25 ethoxy ethyl protecting on a portion of the phenolic and/or cyclohexanol -OH groups. Each of the resists contained an additive of tetrabutylammonium hydroxide, in Examples 1, 1a, 2 and 2a, that additive was present at 0.25 wt % of the resin binder, and in Examples 3 and 3a that additive was present at 0.22 wt % of the resin binder. Each of the resists also contained an additive of a commercially available surface leveling agent

(FC430 from 3M), in Examples 1, 1a, 2 and 2a, that additive was present at 0.13 weight % of the resin binder, and in Examples 3 and 3a that additive was present at 0.50 wt % of the resin binder. In Example 3, the triarylsulfonium PAG was a mixture of triarylsulfonium compounds that can be provided by the procedure of Example 1a of U.S.

5 Patent 5,731,364.

Example 1

A photoresist formulation was prepared by admixing the following components and above-mentioned additives of the specified amounts:

10	<u>Component</u>	<u>Amount:</u>
	1. Resin Binder	18.41 grams
	2. <u>PAG:</u> di-(4-tolyl)-4-octyloxyphenylsulfonium camphorsulfonate	3.23 weight % of resin binder
15		
	3. <u>Solvent:</u> PMA	added to provide a solution at 19 weight % solids
20		

Samples of the resist formulation were stored at temperatures of 4°C, 20°C and 40°C in dark-colored glass bottles for 0 days (control), 7 days and 14 days after resist preparation.

25 Each of the resist formulations was spin coated onto a silicon wafer substrate to a layer thickness of 6990 angstroms and soft-baked on a vacuum hotplate at 90°C for 90 seconds. The dried resist layer was then exposed (GCA XLS 7800 DUV stepper 0.53NA, 0.74 sigma) with CymerKrF Laser), post-exposure baked at 110°C for 90 seconds and developed with 0.26N aqueous tetramethylammonium hydroxide solution for 45 seconds
30 SSP (single spray puddle development).

For the resist formulation samples (i.e., the samples stored for 0, 7 or 14 days after preparation at the above-specified temperatures), no change in photospeed was observed between samples stored at 0, 7 or 14 days at the varying temperatures, thus indicating good storage stability of the resist formulation.

Example 1a (Comparative using iodonium-type PAG)

A comparative photoresist formulation was prepared by admixing the following components and above-mentioned additives of the specified amounts:

10	<u>Component</u>	<u>Amount:</u>
1.	Resin Binder	18.43 grams
2.	<u>PAG:</u> di-(4-t-butylphenyl)iodonium camphorsulfonate	3.10 weight % of resin binder (same molar amount as PAG of Example 1)
15		
3.	<u>Solvent:</u> PMA	added to provide a solution at 19 weight % total solids
20		

The resist samples of this Example 1a were treated and processed in the same manner as described in Example 1 above. Significant photospeed differences were observed among these Example 1a resist samples over storage time.

Specifically, for resist samples stored at 20°C, the following E_o (mj/cm²) values were recorded: sample tested immediately after preparation: $E_o=4.6$; sample tested at 7 days after preparation: $E_o=4.0$; sample tested at 14 days after preparation: $E_o=3.5$.

For resist samples stored at 40°C, the following E_o (mj/cm²) values were

recorded: sample tested immediately after preparation: $E_o=4.6$; sample tested at 7 days after preparation: $E_o=2.2$; sample tested at 14 days after preparation: $E_o=1.7$.

Example 2

- 5 A photoresist formulation was prepared by admixing the following components and above-mentioned additives of the specified amounts:

	<u>Component</u>	<u>Amount:</u>
1.	Resin Binder	18.59 grams
10 2.	<u>PAG:</u> triphenylsulfonium pentafluorobenzenesulfonate	2.21 weight % of resin binder
15 3.	<u>Solvent:</u> PMA	added to provide a solution at 19 weight % total solids

- 20 Samples of the Example 2 resist formulation were treated and processed as described in Example 1 above. For the resist formulation samples (i.e., the samples stored for 0, 7 or 14 days after preparation at the above-specified temperatures), essentially no change in photospeed was observed between samples stored at 0, 7 or 14 days at the varying temperatures, thus indicating good storage stability of the resist formulation.

25 Example 2a (Comparative using iodonium type PAG)

 A comparative photoresist formulation was prepared by admixing the following components and above-mentioned additives of the specified amounts:

	<u>Component</u>	<u>Amount:</u>
1.	Resin Binder	18.41 grams

2. PAG:

di-(4-t-butylphenyl)iodonium
pentafluorobenzenesulfonate

3.18 weight % of resin binder
(same molar amount as PAG of
Example 2)

5

3. Solvent:

PMA

added to provide a solution at
19 weight % total solids

10 Example 2a resist samples were treated and processed in the same manner as
described in Example 1 above. Significant photospeed differences were observed among
these Example 2a resist samples over storage time.

Specifically, for resist samples stored at 20°C, the following E_o (mj/cm²) values
15 were recorded: sample tested immediately after preparation: $E_o=3.5$; sample tested at 7
days after preparation: $E_o=3.1$; sample tested at 14 days after preparation: $E_o=2.9$.

For resist samples stored at 40°C, the following E_o (mj/cm²) values were
recorded: sample tested immediately after preparation: $E_o=3.5$; sample tested at 7 days
20 after preparation: $E_o=2.0$; sample tested at 14 days after preparation: $E_o=1.5$.

Example 3

A photoresist formulation was prepared by admixing the following components
and above-mentioned additives of the specified amounts:

25

Component

Amount

1. Resin Binder

16.22 grams

2. PAG:

triarylsulfonium

30

camphorsulfonate

3.58 weight % of resin binder

3. Solvent:
ethyl lactate added to provide a solution at
16.8 weight % solids

5

Samples of the resist formulation were stored at temperatures of -10°C and 40°C in a dark-colored glass bottle for 10 days after resist preparation.

Each of the resist formulations was spin coated onto a silicon wafer substrate to a layer thickness of 7250 angstroms and soft-baked on a vacuum hotplate at 135°C for 60 seconds. The dried resist layer was then exposed (GCA XLS 7800 DUV stepper 0.53NA, 0.74 sigma) with CymerKrF Laser), post-exposure baked at 140°C for 90 seconds and developed with 0.26N aqueous tetramethylammonium hydroxide solution for 45 seconds SSP (single spray puddle development).

15

Essentially no change in photospeed of the samples was observed during storage, thus indicating good storage stability of the resist formulation.

Example 3a (Comparative using iodonium-type PAG)

20 A photoresist formulation was prepared by admixing the following components and above-mentioned additives of the specified amounts:

	<u>Component</u>	<u>Amount</u>
1.	Resin Binder	16.15 grams
25	2. <u>PAG:</u> di-(4-t-butylphenyl)iodonium camphorsulfonate	4.0 weight % (same molar amount as PAG of Example 3)
30	3. <u>Solvent:</u>	

ethyl lactate

added to provide a solution at
19 weight % solids

Samples of the Example 3a resist formulation were stored at temperatures of 4°C
5 and 50°C in a dark-colored glass bottle for 7 days and 14 days after resist preparation.
These Example 3a resist samples were processed as described in Example 3 above.

Significant photospeed differences were observed among the resist samples over
storage time and temperature. Specifically, for resist samples tested at 4°C for 14 days
10 after preparation: $E_o=3.43$; for resist samples stored at 50°C for 7 days after preparation:
 $E_o=2.22$; for resist samples tested at 50°C for 14 days after preparation: $E_o=1.81$. These
changes in photospeed with storage time and temperature indicate storage instability of
the resist formulation.

15 Examples 4-5 – PAG Syntheses

Example 4 – Preparation of di-(4-tolyl)-4-octyloxyphenylsulfonium 10- camphorsulfonate

A 3-neck flask equipped with a thermometer, a nitrogen outlet and a mechanical
stirrer, was charged with phosphorous pentoxide (8.64g) followed by methanesulfonic
20 acid (85.20g). The resulting mixture was stirred at room temperature for 0.5 hour and
then heated at 50°C for 2-3 hours to obtain a homogeneous suspension. The mixture was
cooled to below 10°C in an ice-water bath and n-octylphenyl ether (21.66g, 0.105mol)
was added. Next, p-tolylsulfoxide (20.03g, 0.10mol) was added with good stirring while
maintaining the temperature of the reaction below 10°C. After stirring for 1 hour, the
25 cooling bath was removed and the reaction was stirred at room temperature for 16 hours.
Thereafter, the reaction mixture was added dropwise to a mixture of ice-water (500mL)
with vigorous stirring. The aqueous mixture was washed with toluene/hexane (3x100mL,
1:1) and extracted with dichloromethane (3x200mL). The combined organic layers were
treated with an aqueous solution of ammonium 10-camphorsulfonate (prepared by
30 neutralization of 10-camphorsulfonic acid (29.04g, 0.125mol) with ammonium hydroxide

(14.53M, 8.6mL, 0.125mol)). The two phase solution was stirred at room temperature for 16 hours. The layers were separated and the aqueous phase extracted with dichloromethane (3 x 200mL). The combined organic layers were washed with water (3 x 200mL) and concentrated in vacuo to give a dark oil which solidified on standing to give a lightly colored solid @ 65g. The solid was triturated in ether-ethylacetate for 18 hours, collected by suction filtration and dried in vacuo to provide the title compound, di-(4-tolyl)-4-octyloxyphenylsulfonium 10-camphorsulfonate, as a white solid.

Example 5 – Preparation of 4-t-butyl-di-(4-tolyl)sulfonium

pentafluorobenzenesulfonate

Part 1: Preparation of 4-t-butyl-di-(4-tolyl)sulfonium bromide

A 3-neck flask equipped with a thermometer, a nitrogen outlet and a mechanical stirrer, was charged with p-tolylsulfoxide (11.52g, 50.0mol). Dichloromethane (100mL) was added and the resulting solution cooled to -78°C . Trimethylsilyl bromide (9.19g, 60.0mmol) was added and the resulting solution stirred at -78°C for 15min and then allowed to warm to 0°C . The mixture was stirred at 0°C for 45min, recooled to -78°C and treated dropwise with a solution of 4-t-butylphenylmagnesium bromide (50 mL of a 2M solution in diethyl ether, 0.10mol). After stirring at -78°C for 1 hour, the mixture was warmed to 0°C and stirred thereat for 1.5hours. The reaction was quenched with 3% aqueous hydrobromic acid and extracted with dichloromethane. The combined dichloromethane extracts were dried in vacuo and the residual oil triturated in diethyl ether to provide a solid. That solid was isolated by suction filtration and dried in vacuo to provide 4-t-butyl-di-(4-tolyl)sulfonium bromide as a white powder.

Part 2: Methathesis of 4-t-butyl-di-(4-tolyl)sulfonium bromide to 4-t-butyl-di-(4-tolyl)sulfonium pentafluorobenzenesulfonate

An aqueous solution of pentafluorobenzenesulfonic acid (2.40g, 9.7mmol) was neutralized by the addition of ammonium hydroxide (14.53M, 0.67mL, 9.7mmol). To this solution was added a solution of 4-t-butyl-di-(4-tolyl)sulfonium bromide (3.52g, 8.5mol, used directly from Part 1 above) in dichloromethane (75mL). The resulting

biphasic mixture was stirred at room temperature overnight. The layers were separated and the aqueous phase extracted with additional dichloromethane (2 x 50mL). The combined organic layers were washed with water and concentrated in vacuo. The residue was triturated in tert-butyl methyl ether for 18 hours and the solid collected by suction
5 filtration and dried in vacuo to provide 4-t-butyl-di-(4-tolyl)sulfonium pentafluorobenzenesulfonate as a white solid.


The foregoing description of the invention is merely illustrative thereof, and it is understood that variations and modifications thereof can be made without departing from
10 the spirit or scope of the invention as set forth in the following claims.

09129113-030498
964030-CT-2760

What is claimed is:

1. A photoresist composition comprising:
 - 1) a component that comprises photoacid-labile groups;
 - 2) a sulfonium photoacid generator compound that is substituted with one or more of a moiety that has at least 2 carbon atoms and is selected from optionally substituted alkyl, optionally substituted alkenyl, optionally substituted alkynyl, optionally substituted heteroalkyl, optionally substituted heteroalkenyl or optionally substituted heteroalkynyl; and
 - 3) a non-hydroxylic solvent, and wherein the composition is at least essentially free of a hydroxylic solvent.
2. The composition of claim 1 where the photoacid generator is substituted with a moiety having 3 or more carbon atoms.
3. The composition of claim 1 where the photoacid generator is substituted with a moiety having 4 or more carbon atoms.
4. The composition of claim 1 wherein the photoacid generator is substituted by one or more alkoxy groups.
5. The composition of claim 1 wherein the photoacid generator is substituted by one or more alkyl groups.
6. The composition of claim 1 wherein the photoacid generator is a triaryl sulfonium salt that has one or more aryl groups substituted by the moieties.
7. The composition of claim 1 wherein the photoacid generator is a triphenyl sulfonium salt that has one or more phenyl groups substituted by the one or more moieties.

8. The composition of claim 1 wherein the photoacid generator is a compound of the following formula:



wherein each R is independently alkyl or heteroalkyl having 2 or more carbon atoms;

wherein each X and Y is independently hydrogen, halo, nitro, cyano, sulfonyl, optionally substituted alkyl, optionally substituted alkoxy, optionally substituted aminoalkyl, optionally substituted alkylthio, optionally substituted alkylsulfinyl, optionally substituted alkylsulfonyl, optionally substituted aryloxy; optionally substituted arylalkyl, optionally substituted alkanoyl, optionally substituted carbocyclic aryl, or optionally substituted heteroaromatic or heteroalicyclic having 1 to 3 rings, 3 to 8 ring members in each ring and from 1 to 3 hetero atoms, with at least one of X and Y being other than hydrogen and different from R;

M is a counter anion; and

n, o or p are each independently an integer of from 1 to 5.

9. The composition of claim 8 wherein X and Y are each different than R, and n, o and p are each equal to 1.

10. The composition of claim 9 wherein R, X and Y are each para-substituents.

11. The composition of claim 1 wherein the photoacid generator is a sulfonium salt that has an arylsulfonate counter anion.

12. The composition of claim 11 wherein the arylsulfonate counter anion is substituted with one or more electron-withdrawing groups.
13. The composition of claim 1 wherein the photoacid generator is a sulfonium salt that has an alicyclic sulfonate counter anion.
14. The composition of claim 13 wherein the alicyclic moiety of the counter anion is substituted with one or more electron withdrawing groups.
15. The composition of claim 1 wherein the photoacid generator is a sulfonium salt that has an acyclic sulfonate counter anion.
16. The composition of claim 15 wherein the acyclic moiety of the counter anion is substituted with one or more electron withdrawing groups.
17. The composition of claim 1 wherein the photoacid labile component is a resin binder of the photoresist composition.
18. The composition of claim 1 wherein the photoacid labile component comprises acetalester or ketalester groups.
19. The composition of claim 1 wherein the photoacid labile component comprises carbonate, ester, ether or imide acid labile groups.
20. The composition of claim 1 wherein the non-hydroxylic solvent is a glycol ether.
21. The composition of claim 1 wherein the non-hydroxylic solvent is propylene glycol methyl ether acetate (PMA).

22. The composition of claim 1 wherein the composition contains less than about 10 weight percent, based on total weight of the composition, of a hydroxylic solvent.

23. The composition of claim 1 wherein the composition contains less than about 5 weight percent, based on total weight of the composition, of a hydroxylic solvent.

24. The composition of claim 1 wherein the composition contains less than about 2 weight percent, based on total weight of the composition, of a hydroxylic solvent.

25. A photoresist composition comprising:

- 1) a component that comprises photoacid-labile groups;
- 2) a sulfonium salt photoacid generator compound that has an arylsulfonate, alicyclic or acyclic sulfonate counter anion; and
- 3) a non-hydroxylic solvent, and wherein the composition is at least essentially free of a hydroxylic solvent.

26. The composition of claim 25 wherein the arylsulfonate, alicyclic or acyclic moiety of the counter anion is substituted with one or more electron-withdrawing groups.

27. A positive-acting photoresist composition comprising:

- 1) a component that comprises photoacid-labile groups;
- 2) a photoactive compound that is a triarylsulfonium salt that has a sulfonate counter anion;
- 3) a hydroxylic solvent.

28. A method for forming a photoresist relief image onto a substrate comprising:

- a) applying a coating layer of a photoresist composition of claim 1 on a substrate;
- b) exposing and developing the photoresist coating layer to provide a relief image of the photoresist composition.

29. A method for forming a photoresist relief image onto a substrate comprising:

- a) applying a coating layer of a photoresist composition of claim 24 on a substrate;
- b) exposing and developing the photoresist coating layer to provide a relief image of the photoresist composition.

30. A method for forming a photoresist relief image onto a substrate comprising:

- a) applying a coating layer of a photoresist composition of claim 26 on a substrate;
- b) exposing and developing the photoresist coating layer to provide a relief image of the photoresist composition.

31. An article of manufacture comprising a substrate having coated thereon the photoresist composition of claim 1.

32. An article of manufacture comprising a substrate having coated thereon the photoresist composition of claim 24.


33. An article of manufacture comprising a substrate having coated thereon the photoresist composition of claim 26.

ABSTRACT OF THE DISCLOSURE

The invention provides positive-acting chemically-amplified photoresist compositions that can provide excellent lithographic performance as well as significantly enhanced storage stability. In one aspect, photoresist compositions are provided that comprise a solvent that is free of hydroxy groups (i.e. non-hydroxylic solvent), a resin binder and a photoactive compound that exhibits enhanced and long-term solubility in the solvent. In a further aspect, resists are provided that are formulated in a hydroxyl-containing solvent such as ethyl lactate and that contains a sulfonium salt photoactive compound that includes a sulfonate counter anion that can provide enhanced storage stability for the resist.

091913-050498

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

1. Application papers are not suitable for scanning and are not in compliance with 37 CFR 1.52 because:
 - ☐ All sheets must be the same size and either A4 (21 cm x 29.7 cm) or 8-1/2" x 11". Pages _____ do not meet these requirements.
 - ☐ Papers are not flexible, strong, smooth, non-shiny, durable, and white.
 - ☐ Papers are not typewritten or mechanically printed in permanent ink on one side.
 - ☐ Papers contain improper margins. Each sheet must have a left margin of at least 2.5 cm (1") and top, bottom and right margins of at least 2.0 cm (3/4").
 - ☐ Papers contain hand lettering.
2. Drawings are not in compliance and were not scanned because:
 - ☐ The drawings or copy of drawings are not suitable for electronic reproduction.
 - ☐ All drawings sheets are not the same size. Pages must be either A4 (21 cm x 29.7 cm) or 8-1/2" x 11".
 - ☐ Each sheet must include a top and left margin of at least 2.5 cm (1"), a right margin of at least 1.5 cm (9/16") and a bottom margin of at least 1.0 cm (3/8").
3. Page(s) _____ are not of sufficient clarity, contrast and quality for electronic reproduction.
4. Page(s) _____ are missing.
5. OTHER: NO Drawings/No Declaration